

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 1 010 540 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
16.07.2003 Bulletin 2003/29

(51) Int Cl.7: **B41M 5/00, B41M 7/00**

(21) Application number: **99204147.5**

(22) Date of filing: **06.12.1999**

(54) Ink jet printing process

Tintenstrahldruckverfahren

Procédé d'impression à jet d'encre

(84) Designated Contracting States:
DE FR GB

(30) Priority: **18.12.1998 US 216350**

(43) Date of publication of application:
21.06.2000 Bulletin 2000/25

(73) Proprietor: **EASTMAN KODAK COMPANY**
Rochester, New York 14650 (US)

(72) Inventors:
• **Kovacs, Csaba A., Eastman Kodak Company**
Rochester, New York 14650-2201 (US)
• **Kung, Teh-Ming, Eastman Kodak Company**
Rochester, New York 14650-2201 (US)

• **Romano, Jr., Charles Eugene,**
Eastman Kodak Company
Rochester, New York 14650-2201 (US)

(74) Representative: **Haile, Helen Cynthia et al**
Kodak Limited
Patent, W92-3A,
Headstone Drive
Harrow, Middlesex HA1 4TY (GB)

(56) References cited:
GB-A- 2 324 800 **US-A- 4 419 388**

• **PATENT ABSTRACTS OF JAPAN vol. 004, no.**
092 (M-018), 3 July 1980 (1980-07-03) & JP 55
049288 A (TEKUSUTAA:KK;OTHERS: 01), 9 April
1980 (1980-04-09)

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

Description

[0001] This invention relates to an ink jet printing process for improving the light stability of an ink jet image formed from an aqueous ink containing a certain cationic dye.

[0002] Ink jet printing is a non-impact method for producing images by the deposition of ink droplets in a pixel-by-pixel manner to an image-recording element in response to digital signals. There are various methods which may be utilized to control the deposition of ink droplets on the image-recording element to yield the desired image. In one process, known as continuous ink jet, a continuous stream of droplets is charged and deflected in an imagewise manner onto the surface of the image-recording element, while unimaged droplets are caught and returned to an ink sump. In another process, known as drop-on-demand ink jet, individual ink droplets are projected as needed onto the image-recording element to form the desired image. Common methods of controlling the projection of ink droplets in drop-on-demand printing include piezoelectric transducers and thermal bubble formation. Ink jet printers have found broad applications across markets ranging from industrial labeling to short run printing to desktop document and pictorial imaging.

[0003] The inks used in the various ink jet printers can be classified as either dye-based or pigment-based. A dye is a colorant which is molecularly dispersed or solvated by a carrier medium. The carrier medium can be a liquid or a solid at room temperature. A commonly used carrier medium is water or a mixture of water and organic co-solvents. Each individual dye molecule is surrounded by molecules of the carrier medium. In dye-based inks, no particles are observable under the microscope. Although there have been many recent advances in the art of dye-based ink jet inks, such inks still suffer from deficiencies such as low optical densities on plain paper and poor light-fastness. When water is used as the carrier medium, such inks also generally suffer from poor water-fastness.

[0004] JP 10-219157 relates to an ink jet ink comprising an aqueous medium, a colorant and a very small amount of glutaraldehyde as a biocide.

[0005] There is a problem with using this ink, however, in that when it is printed on an image-recording element, the resultant image fades when exposed to light over a period of time, i.e., has poor light stability.

[0006] It is an object of this invention to provide an ink jet printing process for improving the light stability of an ink jet image formed from an aqueous ink containing a deprotonated cationic dye. It is another object of the invention to provide an ink jet printing process where the laydown of the hardener applied can be precisely controlled independently of ink laydown and can be applied non-imagewise to the entire element.

[0007] These and other objects are achieved in accordance with the present invention which comprises an ink jet printing process for improving the light stability of an ink jet image comprising:

- a) providing an ink jet recording element comprising a support having thereon an image-recording layer comprising a cross-linkable polymer of gelatin or acetoacetylated poly(vinyl alcohol) and a mordant;
- b) applying liquid ink droplets of a dye on the image-recording layer in an image-wise manner, the dye being a water-soluble deprotonated cationic dye which is capable of being reprotonated to a cationic dye having a N-H group which is part of a conjugated system; and
- c) applying an aqueous solution of a multivalent inorganic salt to the image to cross-link the polymer.

[0008] It was found that when an aqueous solution containing a hardener is applied to a cationic dye-based ink image where the image-receiving layer has a cross-linkable polymer and a mordant, that the light stability of the image is improved.

[0009] This process offers an advantage over incorporating a hardener in an ink since the hardener can be applied in both imaged and non-imaged areas, and the laydown can be precisely controlled independent of ink laydown.

[0010] The hardeners employed in the invention may be used at concentrations ranging from 0.10 to 5.0 weight percent of active ingredient in the aqueous solution, preferably 0.25 to 2.0 weight percent.

[0011] The aqueous hardener solution may also contain, if desired, co-solvents, humectants, surfactants, and other ingredients commonly added to ink jet inks.

[0012] The multivalent inorganic salt hardener that can be employed in the invention include the following (including mixtures thereof): sulfates of a trivalent metal such as aluminum sulfate, iron sulfate, boron sulfate, gallium sulfate, indium sulfate, titanium sulfate, etc., nitrates of iron, aluminum, zinc, etc.

[0013] Specific examples of multivalent inorganic salt hardeners useful in the invention include the following:



- Hardener 1 ferric nitrate
- Hardener 2 aluminum nitrate
- Hardener 3 zinc nitrate
- Hardener 4 zinc sulfate
- Hardener 5 aluminum sulfate

[0014] In a preferred embodiment, the hardener employed in the invention is aluminum sulfate.

[0015] The aqueous hardener solution may be applied to the ink jet image in accordance with the invention in a non-imagewise manner either through a separate thermal or piezoelectric printhead, or by any other method which would apply the hardener solution evenly to the image, such as a spray bar or immersing the element in a bath of hardener. Methods of applying a hardener solution are disclosed in commonly-owned U.S. Patent No. US-B-6176574 filed May 22, 1998, entitled "Printing Apparatus With Spray Bar For Improved Durability" of Wen et al. and U.S. Patent No. US-B-6254230, filed May 22, 1998, entitled "Ink Jet Printing Apparatus With Print Head For Improved Image Quality" of Wen et al.

[0016] Deprotonated cationic dyes useful in the invention which are capable of being reprotonated to a cationic dye having a N-H group which is part of a conjugated system are described in US-A-5,523,274.

[0017] In a preferred embodiment of the invention, the deprotonated cationic dye employed in the invention and the corresponding cationic dye having a N-H group which is part of a conjugated system have the following structures:



wherein:


X, Y and Z form a conjugated link between nitrogen atoms selected from CH, C-alkyl, N, or a combination thereof, the conjugated link optionally forming part of an aromatic or heterocyclic ring;

R represents a substituted or unsubstituted alkyl group from 1 to 10 carbon atoms;

R¹ and R² each individually represents a substituted or unsubstituted phenyl or naphthyl group or a substituted or unsubstituted alkyl group from 1 to 10 carbon atoms; and

n is an integer of from 0 to 11.

[0018] The deprotonated cationic dyes according to the above formula are disclosed in US-A-4,880,769, US-A-4,137,042 and US-A-5,559,076, and in K. Venkataraman ed., The Chemistry of Synthetic Dyes, Vol. IV, p. 161, Academic Press, 1971. Specific examples of such dyes include the following (the λ max values and color descriptions in parentheses refer to the dye in its protonated form):




Dye 1

λ max 556 nm (641 nm)

magenta (cyan)


US-A-4,880,769 (Dye 1)



Dye 2

λ max 459 nm (536 nm)


yellow (magenta)




Dye 3

λ max 459 nm (522 nm)


yellow (magenta)




Dye 4
 λ max 503 nm (621 nm)
 red (blue)




Dye 5
 λ max 379 nm (405 nm)
 yellow (yellow)




Dye 6
 λ max 479 nm (513 nm)
 yellow (magenta)



Dye 7
 λ_{max} 485 nm (495)
 yellow (yellow)



Dye 8
 yellow (magenta)
 US-A-5,559,076 (dye precursor 5)



Dye 9
 (magenta)

[0019] The dyes described above may be employed in any amount effective for the intended purpose. In general, good results have been obtained when the dye is present in an amount of from 0.05 to 1.0 g/m², preferably from 0.1 to 0.5 g/m². Dye mixtures may also be used.

[0020] A mordant is used in the image-recording element used in the invention to fix the deprotonated cationic dye.

For example, there may be used an anionic polymer such as sulfonated and carboxylated polyesters, sulfonated and carboxylated acrylates, poly(vinyl sulfonic acid), poly(vinyl styrene sulfonate sodium salt), sulfonated and carboxylated polyurethanes, sulfonated polyamides, polyolefinic emulsions, carboxylated butadiene, or derivitized anionic gelatin. In a preferred embodiment, the following mordants may be employed in a recording element used in the invention:

Mordant 1	polyester dispersion AQ29 (Eastman Chemical Co.)
Mordant 2	polyester dispersion AQ38 (Eastman Chemical Co.)
Mordant 3	polyester dispersion AQ48 (Eastman Chemical Co.)
Mordant 4	polyester dispersion AQ55 (Eastman Chemical Co.)
Mordant 5	polyester dispersion AQ1045 (Eastman Chemical Co.)
Mordant 6	sulfonated polyester EvCote® EV-LC (EvCo Research Co.)
Mordant 7	carboxylated polyester EvCote® EV-565 (EvCo Research Co.)

[0021] The above mordants may be employed in any amount effective for the intended purpose. In general, good results are obtained when the mordant is present in an amount of from 0.5 to 5 g/m² of element.

[0022] As noted above, the cross-linkable polymer employed in the invention is gelatin or acetoacetylated poly(vinyl alcohol). Gelatin which may be used include the conventional lime-processed ossein, acid-processed ossein or pig skin gelatin. In addition, there are a variety of chemically-modified gelatins formed by reacting the amino group of lysine which can be used. Some functional groups that have been added to gelatin include: phthalate, phenylcarbamy, succinyl, carbamyl, lauryl, and dodecenyl succinyl. There can also be used quaternized gel, silanol modified gel, and graft copolymers of gel with poly(styrene sulfonate), poly(vinylpyrrolidone), and poly(methacrylic acid).

[0023] The acetoacetylated poly(vinyl alcohol) useful in the invention is described in US-A- 4,350,788. These materials are available commercially as Gohsefimer® Z-200 from Nippon Gohsei.

[0024] The image-recording layer used in the process of the present invention can also contain various known additives, including matting agents such as titanium dioxide, zinc oxide, silica and polymeric beads such as crosslinked poly(methyl methacrylate) or polystyrene beads for the purposes of contributing to the non-blocking characteristics and to control the smudge resistance thereof; surfactants such as non-ionic, hydrocarbon or fluorocarbon surfactants or cationic surfactants, such as quaternary ammonium salts; fluorescent dyes; pH controllers; anti-foaming agents; lubricants; preservatives; viscosity modifiers; dye-fixing agents; waterproofing agents; dispersing agents; UV- absorbing agents; mildew-proofing agents; mordants; antistatic agents, anti-oxidants, optical brighteners, and the like. A hardener may also be added to the ink-receiving layer if desired.

[0025] Ink jet inks used in the process of the present invention are well-known in the art. The ink compositions used in ink jet printing typically are liquid compositions comprising a solvent or carrier liquid, dyes, humectants, organic solvents, detergents, thickeners, preservatives, conductivity enhancing agents, anti-kogation agents, drying agents, defoamers, etc. The solvent or carrier liquid can be solely water or can be water mixed with other water-miscible solvents such as polyhydric alcohols. Inks in which organic materials such as polyhydric alcohols are the predominant carrier or solvent liquid may also be used. Particularly useful are mixed solvents of water and polyhydric alcohols.

[0026] A carrier can be present in the ink jet ink and can vary widely, depending on the nature of the ink jet printer for which the inks are intended. For printers which use aqueous inks, water, or a mixture of water with miscible organic co-solvents, is the preferred carrier medium. Co-solvents (0-20 wt. % of the ink) are added to help prevent the ink from drying out or crusting in the orifices of the printhead or to help the ink penetrate the receiving substrate. Preferred co-solvents for the inks employed in the present invention include glycerol, ethylene glycol, propylene glycol, 2-methyl-2,4-pentanediol, and diethylene glycol, and mixtures thereof, at overall concentrations ranging from 5 to 20 wt. % of the ink.

[0027] The support for the ink jet recording element used in the invention can be any of those usually used for ink jet receivers, such as paper, resin-coated paper, poly(ethylene terephthalate), poly(ethylene naphthalate) and microporous materials such as poly polyethylene polymer-containing material sold by PPG Industries, Inc., Pittsburgh, Pennsylvania under the trade name of Teslin®, Tyvek® synthetic paper (DuPont Corp.), and OPPalyte® films (Mobil Chemical Co.) and other composite films listed in US-A-5,244,861.

[0028] The support used in the invention may have a thickness of from 50 to 500 µm, preferably from 75 to 300 µm. Antioxidants, antistatic agents, plasticizers and other known additives may be incorporated into the support, if desired. In a preferred embodiment, paper is employed.

[0029] In order to improve the adhesion of the image-recording layer to the support, the surface of the support may be subjected to a corona-discharge-treatment prior to applying the image-recording layer.

[0030] In addition, a subbing layer, such as a layer formed from a halogenated phenol or a partially hydrolyzed vinyl chloride-vinyl acetate copolymer can be applied to the surface of the support to increase adhesion of the image recording layer. If a subbing layer is used, it should have a thickness (i.e., a dry coat thickness) of less than 2 µm.

[0031] The image-recording layer may be present in any amount which is effective for the intended purpose. In

general, good results are obtained when it is present in an amount of from 5 to 30 g/m², preferably from 8 to 15 g/m², which corresponds to a dry thickness of 5 to 30 µm, preferably 8 to 15 µm.

[0032] The following examples are provided to illustrate the invention.

Example 1

Control Example C-1

Preparation of Receiver A

[0033] A 102 µm poly(ethylene terephthalate) film support was coated with a subbing layer of acrylonitrile-vinylidene chloride-acrylic acid terpolymer latex (0.11 g/m²). On top of the subbing layer was coated a solvent-absorbing layer of lime-processed Ossein photographic gelatin (Eastman Gelatin) (6.05g/m²) Over this layer was coated an ink-receiving layer of Mordant 4 (0.77 g/m²), lime-processed Ossein photographic gelatin (2.42 g/m²) and styrene-butadiene polymeric beads (0.11 g/m²) having an average size of 10 µm.

Preparation of Cyan Ink

[0034] An ink was prepared by dissolving 5 parts by weight cyan dye 1 described above with stirring in a mixture of 60 parts glycerol humectant, 60 parts diethylene glycol humectant, 3 parts of Surfynol® 465 surfactant, 1 part of 10% Proxel® GXL biocide in water, 8 parts of 85 % lactic acid in water (to protonate the dye) and 860 parts of deionized water as the solvent.

Printing

[0035] The top of a black ink cartridge of an Epson 200 ink jet printer was opened with a knife. The Epson ink and the sponge were removed and the cartridge was washed with water and ethanol and dried. The sponge was replaced with a Willtec® (Illbruck Co.) sponge. The cyan ink described above was filtered with a Autovial® 0.45 µm membrane filter (Whatman, Cat. No. AV125UGMF) and the cartridge was filled with the filtered cyan ink. The top of the black cartridge was re-sealed with Permacel® tape (Permacel Company, P-252). A twenty-one step density tablet was printed on Receiver A at 100 % laydown using an Epson 200 printer at 360 dpi resolution.

Light Fade Test

[0036] After the highest density step of the twenty-one step tablet was measured with an X-Rite® densitometer, the strip was exposed for seven days to simulated daylight by a method recommended by the Image Stability Technical Center for standard. 50 klux Daylight exposure (ANSI IT9.9-1990 "Stability of Color Photographic Images" Section 5 Paragraph 5.6 Describes Simulated Indoor Indirect Daylight exposure). After seven days exposure, the optical density of the highest density step was re-measured. To calculate the percent optical density retained, the optical density value at λ-max after seven days light exposure was divided by the optical density value at λ-max before light exposure and the resulting number was multiplied by one-hundred. The results are shown in Table 1.

Invention Example 1

[0037] This example was the same as Control Example C-1 except that after printing, the image was submerged for five minutes in a 4 % solution of Hardener 1 in water. The results are shown in Table 1.

Invention Example 2

[0038] This example was the same as Invention Example 1 except that the hardener was Hardener 2. The results are shown in Table 1.

Invention Example 3

[0039] This example was the same as Invention Example 1 except that the hardener was Hardener 3 The results are shown in Table 1.

Invention Example 4

[0040] This example was the same as Invention Example 1 except that the hardener was Hardener 4. The results are shown in Table 1.

Table 1

Hardener	Retained Optical Density
None (Control C-1)	76
1	95
2	78
3	81
4	85

[0041] The above results show that an ink jet image obtained in accordance with the invention has superior light stability as compared to a control element which was not treated with a hardener solution.

Example 2Control Example C-2Preparation of Receiver B

[0042] A 102 μm poly(ethylene terephthalate) film support was coated with a subbing layer of acrylonitrile-vinylidene chloride-acrylic acid terpolymer latex (0.11 g/m²). On top of the subbing layer was coated a solvent-absorbing layer of Mordant 4 (3.3 g/m²), lime-processed Ossein photographic gelatin (Eastman Gelatin) (3.74g/m²) and styrene-butadiene polymeric beads (0.11 g/m²) having an average size of 10 μm . Over this layer was coated an ink-receiving layer of Mordant 4 (0.44 g/m²) and lime-processed Ossein photographic gelatin (1.76 g/m²).

[0043] Testing was same as in Example 1 but for 14 days.

Invention Example 5

[0044] This example was the same as Control Example 1 except that after printing, the image was submerged for five minutes in a 4 % solution of Hardener 5. The same light stability test and calculation method was employed as in Example 1.

Table 3

Hardener	Retained Optical Density
None (Control)	59
5	89

[0045] The above results show that an ink jet image obtained in accordance with the invention has superior light stability as compared to a control element which was not treated with a hardener solution.

Claims

1. An ink jet printing process for improving the light stability of an ink jet image comprising:

- providing an ink jet recording element comprising a support having thereon an image-recording layer comprising a cross-linkable polymer of gelatin or acetoacetylated poly(vinyl alcohol) and a mordant;
- applying liquid ink droplets of a dye on said image-recording layer in an image-wise manner, said dye being a water-soluble deprotonated cationic dye which is capable of being reprotonated to a cationic dye having a N-H group which is part of a conjugated system; and
- applying an aqueous solution of a multivalent inorganic salt to said image to cross-link said polymer.

2. The process of Claim 1 wherein solution of a multivalent inorganic salt is applied by means of an ink jet print head.
3. The process of Claim 1 wherein said solution of a multivalent inorganic salt is applied by submerging said element in said aqueous solution to cross-link said polymer.
4. The process of Claim 1 wherein said support is paper.
5. The process of Claim 1 wherein said cross-linkable polymer is present in an amount of from 5 to 30 g/m².
6. The process of Claim 1 wherein said mordant is a polyester dispersion in water.
7. The process of Claim 1 wherein said mordant is present in an amount of from 0.5 to 5 g/m².
8. The process of Claim 1 wherein said liquid ink has a water carrier.
9. The process of Claim 1 wherein multivalent inorganic salt is aluminum sulfate.

Patentansprüche

1. Tintenstrahldruckverfahren zur Verbesserung der Lichtstabilität eines Tintenstrahlbildes, wobei das Verfahren folgende Schritte umfasst:
 - a) Bereitstellen eines Tintenstrahl-Aufzeichnungselements, das einen Träger umfasst, auf dem eine Bildaufzeichnungsschicht angeordnet ist, die ein vernetzbares Polymer von Gelatine oder acetoacetyliertem Poly(vinylalkohol) und ein Beizmittel umfasst;
 - b) bildweises Aufbringen flüssiger Tintentröpfchen eines Farbstoffs auf der Bildaufzeichnungsschicht, wobei der Farbstoff ein wasserlöslicher, entprotonierter, kationischer Farbstoff ist, der wieder an einen kationischen Farbstoff mit einer N-H-Gruppe protonierbar ist, die Teil eines konjugierten Systems ist; und
 - c) Aufbringen einer wässrigen Lösung eines mehrwertigen anorganischen Salzes auf das Bild zur Vernetzung des Polymers.
2. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** die Lösung eines mehrwertigen anorganischen Salzes mithilfe eines Tintenstrahldruckkopfes aufbringbar ist.
3. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** die Lösung eines mehrwertigen anorganischen Salzes durch Eintauchen des Elements in die wässrige Lösung zur Vernetzung des Polymers aufbringbar ist.
4. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** der Träger Papier ist.
5. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** das vernetzbare Polymer in einer Menge von 5 bis 30 g/m² vorhanden ist.
6. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** das Beizmittel eine Polyesterdispersion in Wasser ist.
7. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** das Beizmittel in einer Menge von 0,5 bis 5 g/m² vorhanden ist.
8. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** die flüssige Tinte einen Wasserträger umfasst.
9. Tintenstrahldruckverfahren nach Anspruch 1, **dadurch gekennzeichnet, dass** das mehrwertige anorganische Salz Aluminiumsulfat ist.

Revendications

1. Procédé d'impression par jet d'encre pour améliorer la stabilité à la lumière d'une image imprimée par jet d'encre, ce procédé comprenant :

a) la préparation d'un élément d'enregistrement par jet d'encre comprenant un support revêtu d'une couche d'enregistrement d'image comprenant un polymère réticulable de gélatine ou d'alcool polyvinylique acétoacétylé et un mordant ;

b) l'application, conformément à l'image, de gouttelettes d'encre liquide d'un colorant sur ladite couche d'enregistrement d'image, ledit colorant étant un colorant cationique déprotoné soluble dans l'eau qui peut être reprotoné en un colorant cationique ayant un groupe N-H qui fait partie d'un système conjugué ; et

c) l'application d'une solution aqueuse d'un sel inorganique polyvalent sur ladite image pour réticuler ledit polymère.

2. Procédé selon la revendication 1, dans lequel ladite solution d'un sel inorganique polyvalent est appliquée au moyen d'une tête d'impression par jet d'encre.

3. Procédé selon la revendication 1, dans lequel ladite solution d'un sel inorganique polyvalent est appliquée en immergeant ledit élément dans ladite solution aqueuse pour réticuler ledit polymère.

4. Procédé selon la revendication 1, dans lequel ledit support est un papier.

5. Procédé selon la revendication 1, dans lequel ledit polymère réticulable est présent en une quantité comprise entre 5 et 30 g/m².

6. Procédé selon la revendication 1, dans lequel ledit mordant est une dispersion aqueuse de polyester.

7. Procédé selon la revendication 1, dans lequel ledit mordant est présent en une quantité comprise entre 0,5 et 5 g/m².

8. Procédé selon la revendication 1, dans lequel ladite encre liquide comprend un véhicule aqueux.

9. Procédé selon la revendication 1, dans lequel le sel inorganique polyvalent est le sulfate d'aluminium.